

TIP PENE	ISO 845 GUSTINA kg/m ³ ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa min	ISO 1798 IZDUŽENJE PRI KIDANJU % min	ISO 1856 TRAJNA DEFORMACIJA % max 50% sabijenosti
----------	--	---	--	---	---

VISOKO ELASTIČNE PENE - HR PENE

VAPEN HR 2538	25	3.8	70	110	6.5
VAPEN HR 2733	27	3.3	100	100	5.0
VAPEN HR 3530	35	3	100	100	5.0
VAPEN HR 3538	35	3.8	100	100	4.0
VAPEN HR 3746	37	4.6	110	100	4.0
VAPEN HR 4026	40	2.6	120	100	4.0
VAPEN HR 4035	40	3.5	120	100	4.0