

TIP PENE	ISO 845 GUSTINA kg/m ³ ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa min	ISO 1798 IZDUŽENJE PRI KIDANJU % min	ISO 1856 TRAJNA DEFORMACIJA % max 50% sabijenosti
----------	--	---	--	---	---

VISKO ELASTIČNE (MEMORY) PENE

VAPEN LR 2812 P	28	1.2	50	100	4
VAPEN LR 4015 P	40	1.5	50	100	4
VAPEN LR 5016 P	50	1.6	50	100	4
VAPEN LR 5010	50	1.0	50	100	4
VAPEN LR 5010G	50	1.0	50	100	4