

TIP PENE	ISO 845 GUSTINA  kg/m <sup>3</sup> ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa <b>min</b>	ISO 1798 IZDUŽENJE PRI KIDANJU % <b>min</b>	ISO 1856 TRAJNA DEFORMACIJA % <b>max</b> 50% sabijenosti
----------	--	---	--	---	---

JAKO OBOJENE PENE

<b>SPG 1626E</b>	16	2.6	70	100	6
<b>SPG 1832E</b>	18	3.2	70	100	6
<b>SPG 1936E</b>	19	3.6	90	100	5.5