

TIP PENE	ISO 845 GUSTINA kg/m ³ ± 5 %	ISO 3386 TVRDOČA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOČA kPa min	ISO 1798 IZDUŽENJE PRI KIDANJU % min	ISO 1856 TRAJNA DEFORMACIJA % max 50% sabijenosti
----------	--	---	--	---	---

STANDARDNE PENE

VAPEN ST 1620E	16	2.0	80	100	5.6
VAPEN ST 1820E	18	2.0	80	100	7
VAPEN ST 1825E	18	2.5	80	100	5
VAPEN ST 2026E	20	2.6	80	100	4.5
VAPEN ST 2336E	23	3.6	90	100	4
VAPEN ST 2536E	25	3.6	90	100	4.5
VAPEN ST 3040E	30	4.0	100	110	3