

TIP PENE	ISO 845 GUSTINA  kg/m <sup>3</sup> ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa <b>min</b>	ISO 1798 IZDUŽENJE PRI KIDANJU % <b>min</b>	ISO 1856 TRAJNA DEFORMACIJA % <b>max</b> 50% sabijenosti
----------	--	---	--	---	---

### VISKO ELASTIČNE (MEMORY) PENE

VAPEN LR 2812	28	1.2	60	100	4
VAPEN LR 4015 P	40	1.5	60	100	4
VAPEN LR 5016 P	50	1.6	60	100	4
VAPEN LR 5010	50	1.0	60	100	4
VAPEN LR 5010G	50	1.0	60	100	4