

TIP PENE	ISO 845 GUSTINA kg/m ³ ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa min	ISO 1798 IZDUŽENJE PRI KIDANJU % min	ISO 1856 TRAJNA DEFORMACIJA % max 50% sabijenosti
----------	--	---	--	---	---

STANDARDNE PENE

VAPEN ST 1620	16	2.0	80	100	6
VAPEN ST 1820	18	2.0	80	100	5
VAPEN ST 1825	18	2.5	80	100	5
VAPEN ST 2026	20	2.6	80	100	4.5
VAPEN ST 2336	23	3.6	90	100	4
VAPEN ST 2536	25	3.6	90	100	4.5
VAPEN ST 3040	30	4.0	100	110	3.2