

TIP PENE	ISO 845 GUSTINA  kg/m <sup>3</sup> ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa <b>min</b>	ISO 1798 IZDUŽENJE PRI KIDANJU % <b>min</b>	ISO 1856 TRAJNA DEFORMACIJA % <b>max</b> 50% sabijenosti
----------	--	---	--	---	---

**PENE POVEĆANE ELASTIČNOSTI**

VAPEN S 2220	22	2.0	70	130	4
VAPEN S 2516	25	1.6	90	100	4.5
VAPEN S 2528	25	2.8	90	120	3
VAPEN S 3030	30	3.0	90	120	3
VAPEN S 3236	32	3.6	90	120	3
VAPEN S 3530	35	3.0	90	120	3
VAPEN S 3730	37	3.0	90	120	3
VAPEN S 3740	37	4.0	90	120	3