

TIP PENE	ISO 845 GUSTINA kg/m ³ ± 5 %	ISO 3386 TVRDOĆA (CLD) kPa ± 15 %	ISO 1798 ZATEZNA ČVRSTOĆA kPa min	ISO 1798 IZDUŽENJE PRI KIDANJU % min	ISO 1856 TRAJNA DEFORMACIJA % max 50% sabijenosti
----------	--	---	--	---	---

BIOPENE

VAPEN S 2525B	25	2.5	90	100	4.5
VAPEN ST 2030B	20	3.0	80	100	4.5
VAPEN ST 2536B	25	3.6	90	100	4.5
VAPEN ST 3040B	30	4.0	100	110	3.2